

STUDY OF SATURABLE ABSORBER MATERIALS FOR Q-SWITCHING DYE
LASER

NUR FARIZAN BINTI MUNAJAT

A thesis submitted in fulfilment of the
requirements for the award of the degree of
Master of Science (Physics)

Faculty of Science
Universiti Teknologi Malaysia

AUGUST 2005

Dedication to my beloved father, mother, family, dear and friends.....

ACKNOWLEDGMENT

First at all, in humble way I wish to give all the praise to Allah, the Almighty God for with His mercy has given me the strength, keredhaanNya and time to complete this work.

Now, I would like to express my sincere gratitude and appreciation to my supervisor, Associate Professor Dr. Noriah Bidin for her supervision, ideas, guidance and enjoyable discussion throughout this study. I hope all this valuable time and experience will keep in continue.

I would like to acknowledgement the help and kindly assistance of the following persons; Allahyarham En. Nyan Abu Bakar for assisting in carrying out experimental works and colleagues from laser laboratory for their continuing corporation, encouragement and useful comment to complete the work.

Here, I would like to take this opportunity to thanks to UTM-PTP and Universiti Teknologi Malaysia for granting this project through vote, 75341. Without this financial support, this project would not be possible.

Thanks also to all my friends and course mates for their views, concerns and encouragement. Last, but not least, I am grateful to my beloved family for their praying, continuing support, patience, valuable advices and ideas throughout the duration of this research.

ABSTRACT

Q-switching is a technology widely used in lasers to generate short pulses with high peak powers. In practice, Q-switching can be realized with various methods including mechanically by rotating mirror, actively either by acousto-optic or electro-optic method, or passively using a saturable absorber. The first two techniques have their own problems especially the spinning machine and the driver to get a shorter pulse duration. Therefore, passive Q-switch was chosen in this study because it requires less optical element inside the laser cavity and no outside driving circuitry and makes this technique simple and relatively cheaper compared to the other two techniques. Passive Q-switching is a better choice for those applications where compactness of the laser is a prime requirement. The objective of this project is to study and characterize the suitable material to be saturable absorber for passive Q-switching laser. The dye laser was utilized as a source of Q-switching laser. As a preliminary, the laser was calibrated to determine the best performance of laser beam. Various materials including 3, 3'-Diethyloxadicarbocyanine Iodide (DODCI), 1,3'-Diethyl-4, 2'-quinolyloxacarbocyanine Iodide (DQOCI) and 1,1'-Diethyl-4, 4'-carbocyanine Iodide (Cryptocyanine) and Chromium-doped Yttrium Aluminium Garnet (Cr^{4+} : YAG) crystal are employed as a saturable absorber material. The pulse width, the single pulse energy and the peak power of the Q-switched laser output are measured. Two of the tested materials namely 1,3'-Diethyl-4, 2'-quinolyloxacarbocyanine Iodide (DQOCI) and Chromium-doped Yttrium Aluminium Garnet (Cr^{4+} : YAG) crystal demonstrate a good performance to be a saturable absorber. The output characteristics of the passive Q-switch laser possess a uniphase of TEM_{00} mode.

ABSTRAK

Pensuisan-Q merupakan satu teknologi yang digunakan secara meluas dalam teknologi laser untuk menjana denyut pendek yang berkuasa tinggi. Secara praktis, pensuisan-Q boleh dibina dengan pelbagai cara termasuk secara mekanikal dengan kaedah putaran cermin, secara aktif sama ada dengan kaedah akusto-optik atau elektro-optik, atau secara pasif menggunakan penyerap tepu. Dua teknik pertama mempunyai masalah tersendiri terutamanya mesin putaran dan pemacu untuk mendapatkan tempoh denyut yang pendek. Oleh yang demikian, dalam penyelidikan ini pensuisan-Q pasif dipilih kerana ia kurang memerlukan elemen optik yang banyak dalam rongga laser dan tidak memerlukan litar memacu luaran menjadikan teknik ini ringkas dan lebih murah berbanding dua teknik yang lain. Teknik pensuisan-Q merupakan pilihan yang tepat untuk penggunaan yang memerlukan satu system laser yang padat. Objektif penyelidikan ini adalah untuk mengkaji dan melakukan pencirian terhadap bahan yang sesuai untuk dijadikan sebagai bahan penyerap tepu. Laser pencilup telah digunakan sebagai sumber laser pensuisan-Q. Sebagai kajian awal, laser tersebut telah ditentu ukur terlebih dahulu untuk menentukan prestasi terbaik cahaya laser. Pelbagai bahan termasuk 3, 3'-Diethyloxadicarbocyanine Iodide (DODCI), 1,3'-Diethyl-4, 2'-quinolyloxacarbocyanine Iodide (DQOCI) and 1,1'-Diethyl-4, 4'-carbocyanine Iodide (Cryptocyanine) dan Chromium-doped Yttrium Aluminium Garnet (Cr^{4+} : YAG) kristal digunakan sebagai bahan penyerap tepu. Tempoh denyut, tenaga keluaran dan kuasa keluaran laser pensuisan-Q diukur. Dua daripada bahan yang telah diuji, iaitu 3'-Diethyl-4, 2'-quinolyloxacarbocyanine Iodide (DQOCI) dan Chromium-doped Yttrium Aluminium Garnet (Cr^{4+} : YAG) kristal dikenalpasti sebagai bahan yang baik untuk dijadikan sebagai penyerap tepu. Keluaran laser pensuisan-Q adalah sefasa dalam mod TEM_{00} .

TABLE OF CONTENTS

CHAPTER	TITLE	PAGE
	DECLARATION	ii
	ACKNOWLEDGEMENT	iv
	ABSTRACT	v
	LIST OF CONTENTS	vii
	LIST OF TABLES	x
	LIST OF FIGURES	xii
	LIST OF SYMBOLS	xvi
1	INTRODUCTION	
	1.1 Literature Review	1
	1.2 Q-Switching Laser	2
	1.3 Passive Q-Switching	5
	1.4 Research Objective	6
	1.5 Research Scope	6
	1.6 Thesis Outline	7
2	THEORY	
	2.1 Introduction	9
	2.2 Pulsed Dye Laser	9
	2.2.1 Active Medium	10
	2.2.2 Wavelength Selection in Pulsed Dye Lasers	10
	2.2.3 Excitation Method	11

2.3	Q-Switching	14
2.3.1	Pumping Mechanism of Q-Switching	15
2.4	Q-Switching Methods	16
2.4.1	Mechanical Q-Switches	17
2.4.2	Electro-Optic Q-Switches	17
2.4.3	Acousto-Optic Q-Switches	18
2.5	Passive Q-Switches	19
2.5.1	Mechanism Of Bleaching	20
3	METHODOLOGY AND MATERIAL	
3.1	Introduction	24
3.2	Sample Preparation	25
3.2.1	Organic Dyes	25
3.2.2	Cr ⁴⁺ : YAG Crystal	26
3.3	Dye Laser	26
3.3.1	Pulse Detection	28
3.3.2	Mode of Triggering	29
3.4	Image Processing System	31
3.4.1	Processing Software	31
3.5	Calibration of Optimum Laser Performance	33
3.6	Experimental Setup	34
4	DYE LASER	
4.1	Introduction	36
4.2	Externally Triggerring Dye Laser	37
4.3	Diagnose The High Performances of Dye Laser	40
4.3.1	Wavelength	40
4.3.2	Cavity Length	44
4.4	Summary	50
5	PASSIVELY Q-SWITCHED DYE LASER	
5.1	Introduction	51
5.2	Passive Q-Switch With Different Saturable Absorber	52

5.2.1	Organic Dyes Saturable Absorber	52
5.2.1.1	DODCI	53
5.2.1.2	DQOCI	60
5.2.1.3	Cryptocyanine	65
5.2.1.4	Comparison of Organic Dyes Saturable Absorber	70
5.2.2	Cr ⁴⁺ : YAG Crystal Saturable Absorber	75
5.3	Summary	76
6	DIAGNOSE OF PASSIVE Q-SWITCH LASER BEAMS	
6.1	Introduction	78
6.2	Analyzing The Beam	79
6.2.1	Gaussian Fit Analysis	79
6.2.2	Beam Spot	86
6.3	Summary	89
7	CONCLUSIONS AND SUGGESTION	
7.1	Conclusions	90
7.2	Problems And Suggestion	93
	REFERENCES	95
	APPENDIX 1	100

LIST OF TABLES

TABLE NO.	TITLE	PAGE
4.1	Power depending on wavelength of dye laser with Coumarin 500 as a lasing medium	41
4.2	Power depending on wavelength of dye laser with Rhodamine 590 as a lasing medium	41
4.3	Pulse duration of dye laser with Coumarin 500 as lasing medium produced at different cavity length	45
4.4	Pulse duration of dye laser with Rhodamine as lasing medium produced at different cavity length	45
4.5	Pulse Energy of dye laser with Coumarin 500 as lasing medium produced at different cavity length	47
4.6	Pulse Energy of dye laser with Rhodamine 590 as lasing medium produced at different cavity length	47
5.1	Pulse duration of passive Q-switch laser upon concentration of DODCI	53
5.2	Pulse energy of passive Q-switch laser upon concentration of DODCI	55
5.3	Peak Power of passive Q-switch laser upon concentration of DODCI.	58

5.4	Pulse duration of passive Q-switch laser upon concentration of DQOCI.	61
5.5	Pulse energy of passive Q-switch laser upon concentration of DQOCI	63
5.6	Peak power of passive Q-switch laser upon concentration of DQOCI	64
5.7	Pulse duration of passive Q-switch laser upon concentration of Cryptocyannine.	66
5.8	Pulse energy of passive Q-switch laser upon concentration of Cryptocyannine	67
5.9	Peak power of passive Q-switch laser upon concentration of DQOCI	69
5.10	Pulse duration, pulse energy and peak power for different position of saturable absorber	75
6.1	Gaussian width in horizontal and vertical profiles for DQOCI saturable absorber due to working distance.	83
6.2	Gaussian width in horizontal and vertical profiles for Cr^{4+} : YAG saturable absorber due to working distance.	83
6.3	Beam spot perimeter and area due to working distance for passively Q-switched dye laser with Coumarin 500 as a lasing medium	87
6.4	Beam spot perimeter and area due to working distance for passively Q-switched dye laser with Rhodamine 590 as a lasing medium	88

LIST OF FIGURES

FIGURE NO.	TITLE	PAGE
2.1	Energy level diagram of a dye laser	12
2.2	Absorption and fluorescence emission spectrum of a typical organic molecule	13
2.3	Mechanism for dye laser action	14
2.4	Development of a Q-switched laser pulse. (a). The pumping source output, (b). Cavity loss, (c).Population inversion, and (d). Q-switch output.	16
2.5	Mechanical Q-switch (rotating chopper).	17
2.6	Electro-optic Q-switch	18
2.7	Acousto-optic Q-switch.	19
2.8	Saturable absorber Q-Switch	20
2.9	Absorption as a function of incident light intensities for a saturable absorber	21

2.10	Energy-level diagram for most saturable absorber dye molecules in solution	21
2.11	Schematic illustration of the three processes, absorption, spontaneous emission and stimulated emission.	22
3.1	Schematic dimension of Cr^{4+} : YAG crystal	26
3.2	LN120C top view	27
3.3	Dye module Optical Layout	27
3.4	BPX 65 Photo detector Circuit	29
3.5	Block diagram of trigger unit	30
3.6	Experimental set-up for measuring the delay time of the dye laser	30
3.7	CCD Profiler Window	31
3.8	Calibration screen option for Video Test 5.0 Software	32
3.9	Dye laser alignment set-up for calibration	34
3.10	Laser cavity of passively Q-switched dye laser	34
3.11	Schematic diagram of experimental set up for passively Q-Switched dye laser	35
4.1	Pulse of input voltage from trigger unit	37
4.2	(a). Channel 1: Pulse from trigger unit. (b). Channel 2: Pulse from BPX 65 photo detector	38
4.3(a)	Pulse shape of the dye laser with Coumarin 500 as a lasing medium.	39
4.3(b)	Pulse shape of the dye laser with Rhodamine 590 as a lasing medium	39

4.4	Accumulated power of dye laser with Coumarin 500 upon on wavelengths	42
4.5	Accumulated power of dye laser with Rhodamine 590 upon on wavelength	43
4.6	The pulse duration and output power versus cavity length of passively Q-switched Rhodamine 590 dye laser.	46
4.7	The output energy of dye laser upon cavity length with different lasing medium	48
4.8	The pulse duration and output power versus cavity length of passively Q-switched Rhodamine 590 dye laser.	49
5.1	Pulse Duration versus concentration of DODCI on different lasing medium	54
5.2	Pulse Energy versus concentration of DODCI on different lasing medium	55
5.3	Graph natural logarithm of pulse energy versus concentration	57
5.4	Peak Power versus concentration of DODCI on different lasing medium	59
5.5	Graph natural logarithm of peak power versus concentration	60
5.6	Pulse Duration versus concentration of DQOCI on different lasing medium	61
5.7	Graph natural logarithm of pulse duration versus concentration	62
5.8	Pulse Energy versus concentration of DQOCI on different lasing medium	63
5.9	Peak Power versus concentration of DQOCI on different lasing medium	65
5.10	Pulse Duration versus concentration of Cryptocyanine on different lasing medium	66

5.11	Pulse Energy versus concentration of Cryptocyanine on different lasing medium	68
5.12	Peak Power versus concentration of Cryptocyanine on different lasing medium	69
5.13(a)	Figure 5.13(a): Pulse duration versus concentration of different saturable absorber materials	70
5.13(b)	Pulse duration versus concentration of different saturable absorber materials	71
5.14(a)	Pulse energy versus concentration of different saturable absorber materials	72
5.14(b)	Pulse energy versus concentration of different saturable absorber materials	73
5.15(a)	Peak power versus concentration of different saturable absorber materials	74
5.15(b)	Peak power versus concentration of different saturable absorber materials	74
6.1	Gaussian profile of passive Q-switch laser beam. (a) Vertical profile, (b). Horizontal profile	80
6.2	Beam Profile of Q-switching laser; (a). Three-dimensional image shows the distribution of Gaussian beam profile (b). Two-dimensional image.	81
6.3	Correlation upon working distances for DQOCI saturable absorber.	85
6.4	Correlation upon working distances for Cr^{4+} : YAG saturable absorber.	85
6.5	Two-dimensional image of passively Q-switched dye laser using DQOCI upon different working distance	86
6.6	Two-dimensional image of passively Q-switched dye laser using Cr^{4+} : YAG crystal upon different working distance	87
6.7	Beam spot area against working distance	88

LIST OF SYMBOLS

Q	-	Quality factor
F	-	Photon flux of the incident light
σ_{12}	-	Absorption cross section
W_{12}	-	Absorption probability
σ_{21}	-	Stimulated emission cross section
m	-	Grating order
λ	-	Wavelength
d	-	Grating constant
θ	-	Angle between the grating and the laser gain axis
I	-	The intensity of a pixel at location x
$i(h, v)$	-	The intensity at location (h, v)
V	-	The maximum intensity of the fitted Gaussian curve (Peak Intensity)
C	-	The centre of the Gaussian fit peak (Centroid)
σ	-	The radius of the Gaussian fit curve at the $1/e^2$ intensity level (diameter)

CHAPTER 1

INTRODUCTION

1.1 Literature Review

Human beings are really clever in making use of different kinds and forms of energy. Laser material processing relies on laser systems of desired properties. An inspiring thing in laser processing is the application of ultra-short pulsed lasers. Ultrafast lasers can give scientist opportunities to probe the behavior of matter when exposed to intense radiation and do studies in fields such as astrophysics, general relativity and quantum mechanics.

This ultrafast laser currently enable scientist to observe the occurrence of the fastest chemical reaction (Kodymova *et al.*, 2004). This is an advanced technology used for ionizing all material within a small area without any heat or mass flow affecting the surrounding area (Charschan, 1972) and carry out precise micromachining (Liu *et al.*, 1997). This technology is also used to design high density, high-speed communications networks, which an ultrafast laser's bandwidth is equivalent to millions of telephone calls. Another application is to design compact particle accelerators and generate fusion energy (Lerner, 1998).

The ultrafast lasers can also imitate the conditions at the center of stars allowing astrophysicists to experiment with possible ways in which stars form and explode in supernovas. These high powered lasers can focus the power of all sunlight falling on Earth onto a spot a tenth of a millimeter on a side, accelerate electrons close to speed of light and generate pressures hundreds of times those of light and create magnetic fields a billion times of Earth (Lerner, 1998). One way of achieving these high power pulses with short duration is by Q-switching technique.

1.2 Q-switching Laser

The power output may be increased by Q-switching, which is achieved by exciting the laser medium so that a population inversion occurs but delaying the application of feedback from the axial mirrors (Hellwarth, 1961). On the simplest way, we can define the Q-switching as a method of using an optical switch inside the laser cavity. This optical switch has two states; it's open when the radiation pass through the switch undisturbed and closed when the radiation cannot pass through the switch. Switching the laser system means transferring the system from on to off or the other way.

The possibility of Q-switching laser was first proposed by Hellwarth in 1961. In practice, Q-switching can be achieved by deflecting the beam at the high reflecting mirror mechanically (Collins and Kisliuk, 1962) or by acousto-optic (Koechner, 1976) or electro-optic (Hellwarth and McClung, 1962) devices or by using an opaque saturable absorber (Soffer, 1964) that bleaches transparent when the fluorescent light output reaches a given level. McClung and Hellwarth made the first experimental observation of Q-switched pulse behavior in 1962 using an electro-optical Q-switch in a ruby laser.

Electro-optic Q-switches employ materials that exhibit birefringence under an applied electric field (Klein, 1998). The advantages of this pure electronic control of Q-switching are many. Such as, the fast switching times, the precise control over, and flexibility of Q-switching and ease to synchronization of the modulation with electronics and measuring apparatus. However, the existence of a Kerr cell (or other electronically controlled switching) inside the laser cavity has presented many problems. They are usually fabricated from crystal such as KDP or LiNbO_3 , which are hygroscopic and prone to damage, by the laser beam. The polarization requirements mean that the laser beam must be polarized. These Q-switches also require some cleverness in the design of the electrical signal without transients. This combination of factors means that the electro-optic Q-switches are typically used in high peak power pulsed lasers, as well as in high gain CW lasers.

Acousto-optic Q-switches, which employ materials such as quartz that exhibit a change in the index of refraction when the material is acoustically excited have the advantages of being low-loss elements when not Q-switching. In contrast with the electro-optic crystals, acousto-optic crystals have high damage thresholds and are typically not hygroscopic. However, the Q-switches generally require high-power RF power supplies at 20 to 60 W, 50 to 150 MHz. This combination of factors means that acousto-optic Q-switches are typically used in low-gain cw lasers. Their most common application is in continuous wave Nd: YAG Q-switched and mode-locked laser systems (Koechner, 1976).

Another method to Q-switch a laser cavity is incorporating a mechanical device within the cavity that blocks the laser beam. The first mechanical Q-switch used a rotating chopper (Collins and Kisliuk, 1962). However, the choppers are slow and vibration-prone, and such techniques were soon abandoned in favor of rotating mirrors and prisms (Benson and Mirachi, 1964). With rotating mirrors, the approach is to spin the mirror using high-speed motor. Such designs usually incorporate a multisided mirror or multiplicative optical geometries so that several reflections are possible for each rotation (Daly and Sims, 1964). However, rotating mirror Q-switches are prone to

alignment difficulties because each face of the mirror must be aligned to within a fraction of miliradian. Although the mechanical Q-switches are the simplest and less expensive, the high rotational speed means that the devices are noisy and process relatively short lifetimes. Furthermore, mechanical components are not robust in harsh environment.

The first three methods of Q-switching are active types, where the switching of the laser light occurs externally. Besides the active type, which is difficult to implement, complex for installation, alignment and operation, laser also can be switching passively. Passive Q-switching received its name from the action of generated radiation itself (Smith and Sorokin, 1966). This technique potentially offers an advantage of low cost, reliability and emission of pulses with a relatively narrow linewidth (Koechner, 1976). It is also simple in fabrication and operation since it requires no high voltages or fast electro-optic devices. Passive Q-switches can be used with pulse pumped systems only because a CW pumped laser never produces sufficient fluorescence to bleach the dye (Kuhn, 1998).

As summary, the reading of all the papers and articles on Q-switching applications and techniques has driven us even stronger to study, diagnose and characterize the fundamental of Q-switching laser. Although it can be achieved by various techniques, this study on passive Q-switching laser and the focus of this research work will be on the materials used as saturable absorber and how to improve the laser outputs.

1.3 Passive Q-switching

Passive Q-switching laser exploits the bleaching of saturable materials. The rising flux within the laser is capable of decreasing the absorptivity of certain saturable absorber placed in the laser cavity. The sudden decrease of absorption has the same effect as the removal of an obstacle in the path of the beam. When properly adjusted, these lasers containing saturable materials trigger themselves to emit a giant pulse.

In the earliest experiments with saturable absorber, Master and Murray (1965) who used an absorbing dye smeared on a microscope slide, and Grant (1963), who used an aluminized Mylar film, produced light pulses of quality and efficiency comparable to that achieved with Kerr cell switches (Geller *et al.*, 1963). However, the absorber was always damaged. The optical saturation in these instances was presumably caused by the evaporation of the thin absorber so as to render the absorber transparent. Subsequently, saturable absorbers have been found which show little or no damage after producing a good quality giant pulse (Soffer, 1964; Sorokin *et al.*; 1964, Kafalas *et al.*, 1964; Bret and Gires, 1964). These employ the saturation of some transition which, because it has a high absorption cross section per absorbing molecule at the laser frequency, requires relatively for photons absorbed, rendering their normal value.

Sorokin *et al.* (1964) found that metalphthalocyanine dyes, dissolved in either nitrobenzene or chlornaphthalene (the latter showed some deterioration after several pulses) produced good giant pulses when placed inside the laser cavity. Apparently, the threshold pump energy was not appreciably changed (the actual value was not given). Soffer (1964) has achieved giant pulses of exceptional spectral purity and normal energy content using a saturable absorber of dilute Cryptocyanine. To produce these high quality pulses, 3000 J pump energy was required, as compared to 900 J for normal operation. Kafalas *et al.* (1964) have also used an absorber of Cryptocyanine (dissolved in methanol) to achieve giant pulse outputs. No deterioration of the Cryptocyanine was observed.

All of works explained above are passively Q-switched solid-state laser. Braveman (1975) have demonstrated the first and only passive Q-switching for Nitrogen-laser-pumped-dye-laser. He used a DODCI as a saturable absorber inside the dye laser cavity (the actual solvent type and concentration value was not given). This experiment produces single high-repetition-rate high peak power tunable subnanosecond pulses. However, this experimental set-up makes used a wide space in the laser cavity. The Avco model C950 nitrogen laser source used in this study showed a thermal distortion dominated the mode structure after 50 pulses per second (pps).

1.4 Research Objective

The main objective of this research is to study the saturable absorber material for passively Q-switched nitrogen-laser-pumped-dye-laser. This includes diagnosing the dye laser in order to utilize the system at its optimum performance. Then, characterize the output of Q-switching laser by altering some laser parameters.

1.5 Research Scope

Several materials are determined as saturable absorbers. The dye laser pumped by nitrogen laser is utilizing as a source to be switched. The dye laser cavity is aligning to get its best performance. An external trigger unit builds for the dye laser in order to get a single shot. The photodetector also builds to detect the laser beam.

1.6 Thesis Outline

This thesis is divided into 7 chapters. The first chapter is the review of some applications of Q-switching laser. Previous research related to miscellaneous Q-switching methods and passive Q-switching also presented. This chapter also emphasizes the aim of the research.

Chapter II reviews the background or the theory related to the research. This will cover the basic theory of Q-switching such as quality factor, Q and pumping mechanism. This chapter also explains the various methods of Q-switching and briefly describes the mechanism of passive Q-switching.

Chapter III describes the sample preparation and methodology for passively Q-switched dye laser. This would include image processing software and experimental setup.

Chapter IV discusses the diagnosed results of dye laser. Various laser parameters are tested such as wavelength, cavity length, working distance and repetition rate in order to determine the current performances of dye laser as a source to be switched.

In chapter V, the pulse width and output energy of passively Q-switched dye laser in various manners are presented. These experimental results were compared with the current standard dye laser performances.

Chapter VI presents the diagnostic analysis of passive Q-switches beam. BeamStar CCD Laser Beam Profiler was utilized as diagnostic system.

Finally, the conclusions of the project are made in chapter VII. includes the summarization of the whole project, the problems involved and experience during performances of the project and some works to be carried out in the near future are suggested.

greatly increase the light power density in the dye. This effect can minimize by working with a fairly thin dye cell.

As mentioned earlier, this research is an initial stage of gaining the knowledge of Q-switching using saturable absorber. Dilute dye saturable absorber are not only effective media for initiation of passive Q-switching, but also have the advantages that their strength can be accurately controlled and varied continuously. Actually, the saturable absorber can also be used in mode-locking mode, which is another technique to produce shorter pulse. Therefore, further studies can be carried out in order to get more information about the saturable absorber material, growing interest in the shortest pulse. Hopefully, all the efforts and experimental works in this study will be a good reference for future work and come out with new bright ideas.

REFERENCES

- Braverman, L.W. (1975). Controlled Passive Q-Switched For The N₂-Laser-Pumped Dye Laser. *J. of Appl. Phys. Lett.*, 27(11): 602-604
- Bret, G. and Gires, F. (1964). Giant-Pulse Laser and Light Amplifier Using Variable Transmission Coefficient Glasses As Light Switches. *Appl. Phys. Lett.* 4 (10): 175-176
- Collins R. J. and Kisliuk P, (1962). Control of population inversion in pulsed optical masers by feedback modulation. *J. Appl. Phys.* 33 (6): 2009-2011
- Charschan, S.S. (1972). *Lasers in Industry*. New York: Western Electric Series
- Daly, R. and Sims, S. D. (1964). An improved method of mechanical Q-switching using total internal reflection. *Appl. Opt.* 3(9): 1063-1066
- Degiorgio, V and Potenza, G. (1965). Saturation Effects in The Absorption of The Laser Light by Organic Dyes (1966). *Nuovo Cimento*, 41B: 254-257
- Degiorgio, V and Potenza, G. (1967). Energy Losses in a Passive Q-switched Ruby Laser. *IEEE J. of Quantum Electronics* 3(2): 59-65

- Duarte, F.J. and Hillman, L.W. (1990). *Dye Laser Principles With Application*, Edited by F.J. Duarte and L.W. Hillman. Quantum Electronics-Principles and Applications, edited by P.F. Liao and P.L. Kelley. Academic Press: San Diego.
- Hellwarth, R. W. (1966). *Q modulation of laser*. *Lasers* 1. A. K. Levine ed. New York: Marcel Dekker Inc. 253
- Hellwarth, R.W. (1961). *Control of Fluorescent Pulsation*. *Advanced in Quantum Electronics*. J. R. Singer ed. New York: Columbia University Press. 334-341
- Hellwarth, R.W. and McClung, F.J. (1962). *Giant Pulsations from Ruby*. *J. Appl. Phys.* 33 (3): 838-841
- Kafalas, P., Mastery, J.I. and Murray, E.M.E. (1964). Photosensitive Liquid used as a Nondestructive Passive Q-Switch in a Ruby Laser. *J. of Appl. Phys.*, 35(8): 2349-2350
- Kagan, M. R. (1968). *Organic Dye Lasers*. *Laser Focus*, 4: 26-27
- Kodymova, J., Spalek, O., Jurasek, V. and Censky, M. (2004). Advances in The Development of Chemical Oxygen-Iodine Laser. *Czechoslovak J. of Phys.* 54 (5): 561-574
- Koechner, W. (1976). *Solid-State Laser Engineering*. New York: Springer-Verlag
- Koechner, W. and Bass, M. (2003). *Solid-State Laser Laser*. New York: Springer-Verlag
- Kuhn, K. J. (1998). *Laser Engineering*. Upper Saddle River, N. J.: Prentice Hall

- Laser Photonics Inc.(1991), LN120C Nitrogen Laser: Operating Manual. Florida: Operator's Manual.
- Laud, B. B. (1985). *Lasers and non-linear optics*. New Delhi: Wiley Eastern
- Lerner, EJ. 1998. "Ultrafast Lasers Deliver Powerful, Precise Pulses." *Laser Focus World*, December: 77-79
- Liu, X, Du.D. and Mourou G. (1997). Laser Ablation and Micromachining with Ultrashort Laser Pulses. *IEEE J. of Quantum Electronics* 33(10): 1706-1717
- Luxon, J.T and Parker, D. E. (1992). *Industrial Lasers and Their Applications*. New Jersey: Prentice Hall. 113-114
- Master, J. I and Murray, E. M. E (1965). Comparison of Passive Q-Switch Components and Observations of Scattering Effects. *Proc. IEEE* 53: 76-79
- Ophir Optronics LTD.(1991). BeamStar CCD Laser Beam Profiler for Windows. Jerusalem: User Manual
- Ross, I. N. and Gates, J. W. C. (1973). A Small Ruby Laser with a Simple Rotating mirror Q-switch. *J. Phys. E:Sci. Instrum.* 6: 125-127
- Shimony, K, Kalisky, Y and Chai, B. H. T (1995). Cr^{4+} : YAG as Passive Q-Switch for Pulsed Nd: YAG Laser. *Opt. Material* 4: 547-551
- Siegman, A. E. (1964). Design Considerations for Laser Pulse Amplifiers. *J. Appl. Phys.* 35: 460-463
- Smith, W. V. and Sorokin, P. (1966). *The Laser*. New York: McGraw- Hill Int.

- Soffer, B. H. (1964). Giant Pulse Laser Operation by A Passive, Reversibly Bleachable Absorber. *J. Appl. Phys.*, 35: 25-28
- Soffer, B. H. and Hoskins, R. H. (1964). Generation of Giant Pulses from a Nd-laser by a Reversible Bleachable Absorber. *Nature* 204: 276-279
- Soffer, B. H., and McFarland, B. B. (1967). Continuously tunable, narrowband, organic dye lasers. *App.. Phys. Lett.* 10(10): 266-267
- Sorokin, P. P., Luzzi, J. J., Lankard, J. R. and Pettit, G. D. (1964). Ruby Laser Q-switching Elements Using Phthalocyanine Molecules in Solution. *IBM J. Res. Develop.* 8: 182-184
- Svelto, O. (1976). *Principles of Lasers*. New York: Plenum Press
- Ter-Mikirtychev, V. V., McKinnie, I. T., Warrington, D. M., Kalisky, Y. and Pollack, S. A (1997). Laser and Absorption Saturation Measurements of Cr^{4+} crystals, Pumped by Broadband Pulsed 940 nm Radiation. *Opt. & Lase Tech.* 29(7): 407-409
- Thyagarajan, K. and Gahatak, A. K. (1981). *Lasers: Theory and Applications*. New York: Plenum Press
- Wagner, W. G and Lengyel, B. A. (1963). Evolution of the giant pulse in a laser. *J. Appl. Phys.* 34: 2042-3045
- Wilson, J. and Hawkes, J. F. B. (1983). *Optoelectronics An Introduction*. Prentice Hall Int.

Xingyu Z. Shengzi Z. Qingpu W. Yaogang L. and Jiyang W. (1994). Optimization of Dye Q-switched Lasers. *IEEE J. of Quantum Electronics*, 30 : 905-908

PRESENTATION AND CONFERENCES

1. Nur Farizan Munajat and Noriah Bidin., **Q-Switched by Saturable Absorber**, Annual Fundamental Science Seminar 2004 (AFSS 2004), 14 June – 15 June 2004, Skudai, Johor
2. Nur Farizan Munajat.and Noriah Bidin., **Q-Switching Dye Laser by Saturable Absorber**, Malaysian Science and Technology Congress 2004 (MSTC 2004), 5 – 7 October 2004, Kuala Lumpur
3. Nur Farizan Munajat and Noriah Bidin., **Diagnose of Q-Switching Nitrogen-Laser-Pumped-Dye-Laser**, The XXI Regional Conference and Workshop on Solid State Science & Technology (RCWSST 2004), 10th – 13th October 2004, Kota Kinabalu, Sabah